

Polydopamine Nanoparticles Functionalized Electrochemical DNA Aptasensor for Serum Glycated Albumin Detection

Pornsuda Maraming ¹, Nang Noon Shean Aye ¹, Patcharee Boonsiri ², Sakda Daduang ³ and Onanong Buhome ⁴ and Jureerut Daduang ^{1,*}

¹ Centre for Research and Development of Medical Diagnostic Laboratories, Faculty of Associated Medical Sciences, Khon Kaen University, Khon Kaen 40002, Thailand

² Department of Biochemistry, Faculty of Medicine, Khon Kaen University, Khon Kaen 40002, Thailand

³ Division of Pharmacognosy and Toxicology, Faculty of Pharmaceutical Sciences, Khon Kaen University, Khon Kaen 40002, Thailand

⁴ Department of Medical Technology, Faculty of Allied Health Sciences, Nakhon Ratchasima College, Nakhon Ratchasima 30000, Thailand

* Correspondence: Correspondence: jurpoo@kku.ac.th

Table S1. Hydrodynamic diameter and polydispersity index (PDI) of PDA-NPs synthesized at different pH.

	The synthesized PDA-NPs under different pH Tris buffer	Hydrodynamic diameter (DH in nm)	PDI
1.	pH 8.5	286.1 ± 1.701	0.258
2.	pH 9.5	142.2 ± 1.595	0.123
3.	pH 10.5	118.0 ± 1.912	0.126