

Supplemental Material 2. Results of the cement thickness analysis performed for the twelve samples of CO veneers versus the twelve samples of CR veneers, displayed in percentages of the total covered prepared surface area.

Sample of each group	Intervals of cement width w (μm)	Covered area of the surface S (%)	
		Group 1, CO veneers	Group 2, CR veneers
1	0 – 120	74.14	83.49
	120 – 400	25.95	14.86
2	0 – 120	46.08	71.48
	120 – 400	54.02	28.67
3	0 – 120	77.06	75.46
	120 – 400	22.94	24.60
4	0 – 120	65.89	81.98
	120 – 400	34.11	18.02
5	0 – 120	73.59	85.05
	120 – 400	26.41	14.95
6	0 – 120	59.63	79.84
	120 – 400	40.37	20.16
7	0 – 120	63.78	88.20
	120 – 400	36.22	11.80
8	0 – 120	49.30	84.63
	120 – 400	50.70	15.37
9	0 – 120	68.48	80.19
	120 – 400	31.52	19.81
10	0 – 120	59.41	82.79
	120 – 400	40.59	17.21
11	0 – 120	72.83	85.73
	120 – 400	27.17	14.27
12	0 – 120	64.51	79.96
	120 – 400	35.49	20.04