

Block Copolymer Micelles Encapsulating Au(III) Bis(dithiolene) Complexes as Promising Nanostructures with Antiplasmodial Activity

Joana F. Santos ¹, Raquel Azevedo ², Miguel Prudêncio ², Fernanda Marques ^{1,3}, Yann Le Gal ⁴, Dominique Lorcy ⁴, Célia Fernandes ^{1,3*}

¹Centro de Ciências e Tecnologias Nucleares, Instituto Superior Técnico, Universidade de Lisboa, Estrada Nacional 10, km 139.7, 2695-066 Bobadela LRS, Portugal

²Instituto de Medicina Molecular João Lobo Antunes, Faculdade de Medicina, Universidade de Lisboa, Av. Prof. Egas Moniz, 1649-028 Lisboa, Portugal

³Departamento de Engenharia e Ciências Nucleares, Instituto Superior Técnico, Universidade de Lisboa, Estrada Nacional 10, km 139.7, 2695-066 Bobadela LRS, Portugal

⁴Institut des Sciences Chimiques de Rennes-UMR 6226, Université de Rennes, CNRS, ISCR, F-35000 Rennes, France

Table of Contents

Figure S1.	2
-------------------	----------

PQ, AuSe and AuS were dissolved in DMF, to afford 2.0 g L⁻¹ solutions. These solutions were diluted to prepare serial concentrations corresponding to 0.01 – 0.06 mg mL⁻¹, in the case of PQ, and 0.001 – 0.02 mg mL⁻¹, in the case of AuSe and AuS. The solutions were analyzed by UV-Vis spectrophotometry and the calibration curves were established.




Figure S1. Calibration curves of A) PQ at $\lambda = 364$ nm; B) AuSe at $\lambda = 393$ nm and C) AuS at $\lambda = 364$ nm.