

Supplementary Materials

Impact of Bis-O-Dihydroferuloyl-1,4-Butanediol Content on the Chemical, Enzymatic and Fungal Degradation Processes of Poly(3-Hydroxybutyrate)

Quentin Carboué*, Sami Fadlallah *, Yasmine Werghi, Lionel Longé, Antoine Gallos, Florent Allai and Michel Lopez

URD Agro-Biotechnologies Industrielles (ABI), CEBB, AgroParisTech, 3 Rue des Rouges-Terres, 51110 Pomacle, France; yasmine.werghi1@gmail.com (Y.W.); lionel.longe@agroparistech.fr (L.L.); antoine.gallos@agroparistech.fr (A.G.); florent.allais@agroparistech.fr (F.A.); michel.lopez@agroparistech.fr (M.L.)

* Correspondence: quentin.carboue@agroparistech.fr (Q.C.); sami.fadlallah@agroparistech.fr (S.F.).




Figure S1. ^1H NMR (CDCl_3) spectra of PHB/BDF 40 w% and PHB.

PHB : ^1H NMR (300 MHz, CDCl_3 , δ ppm): 5.25 (dd, $J = 12.7, 6.3$ Hz, 1H), 2.78 – 2.37 (m, 2H), 1.27 (d, $J = 6.2$ Hz, 3H).

BDF : ^1H RMN (400 MHz, CDCl_3 , δ ppm): 6.82 (2H, d, $J = 8$, H₃), 6.68 (4H, m, H_{4,6}), 5.60 (2H, s large, H₁, Ar OH), 4.06 (4H, m, H₁₂), 3.85 (6H, s, H₈), 2.87 (4H, t, $J = 8$, H₉), 2.59 (4H, t, $J = 8$, H₁₀), 1.62 (4H, m, H₁₃).




Figure S2. ^1H NMR (CDCl_3) spectrum of β -hydroxybutyric acid.




Figure S3. ^1H - ^1H COSY (CDCl_3) of PHB/BDF (40 w%) after 32 h of degradation with NaOH solution (0.25 M).




Figure S4. ^1H NMR (CDCl_3) spectra of powders of PHB blends after 7 days of reaction with 5.8 mg. mL^{-1} of Lipopan[®] 50 BG at pH = 7.4, 37 °C and stirred at 50 rpm.




Figure S5. Pictures of the PHB film a./ at t0 and b./ after 4 weeks in the soil samples c./ microscopic observation of *A. elegans*, the aseptate hyphae and sporangia are visible.