

Supplementary Materials: Synthesis of Novel Cobalt-Containing Polysilazane Nanofibers with Fluorescence by Electrospinning

Qian Zhang, Dechang Jia, Zhihua Yang, Xiaoming Duan, Qingqing Chen and Yu Zhou




Figure S1. SEM images of electrospun fibers of 12 wt % PCSN solution. It seems that 12 wt % polymer solutions are not suitable for spinning and resulting in electrospaying, powder or fibers with beads morphology.




Figure S2. SEM images of electrospun fibers of 12 wt % PCSN solution. Figures S1 and S2 are the same concentration of PCSN, but with different resolution images.