

Supplementary Materials

AuAg Nanoparticles Grafted on TiO₂@N-Doped Porous Carbon: Improved Depletion of Ciprofloxacin under Visible Light through Plasmonic Photocatalysis

Marta Jiménez-Salcedo ¹, Miguel Monge ^{1,2,*} and María Teresa Tena ^{1,*}

¹ Department of Chemistry, University of La Rioja, C/Madre de Dios 53, E-26006 Logroño, Spain; marta.jimenez@aurea.unirioja.es

² Centro de Investigación en Síntesis Químicas (CISQ), University of La Rioja, C/Madre de Dios 53, E-26006 Logroño, Spain

* Correspondence: miguel.monge@unirioja.es (M.M.); maria-teresa.tena@unirioja.es (M.T.T.)




Figure S1. Size histograms of nanohybrids 2–4.




Figure S2. TEM images of nanohybrid AuAg-PVP-TiO₂ 4.




Figure S3. Survey XPS spectrum for nanohybrids 1–3.




Figure S4. Narrow XPS spectrum for Ti 2p, O 1s, C 1s and N 1s in nanohybrid 1.

Table S1. Deconvolution of the XPS high-resolution peaks (binding energy in eV) for nanohybrids 1–3.

	C 1s	N 1s	Ti 2p	O 1s	Au 4f	Ag 3d
1	285.0, 286.4, 288.8	400.2	458.8, 464.6	530.0, 531.3	-	-
2	285.0, 286.3, 288.8	400.4	458.8, 464.6	529.8, 530.9	83.5, 84.4, 87.2, 87.4	367.6, 373.6
3	285.0, 286.3, 288.5	399.4	458.7, 464.6	530.0, 531.3	83.4, 83.8, 87.1, 87.2	367.5, 373.5

Table S2. At% and wt% data for nanohybrids 1–3.

	C 1s	N 1s	Ti 2p	O 1s	Au 4f	Ag 3d
1						
at.%	21.11	0.16	22.78	55.95	-	-
wt.%	11.31	0.10	48.66	39.93	-	-
2						
at.%	20.98	0.32	21.98	56.50	0.09	0.13
wt.%	11.23	0.20	46.89	40.27	0.79	0.62
3						
at.%	20.84	0.47	21.52	56.77	0.17	0.22
wt.%	11.11	0.29	45.74	40.31	1.49	1.05




Figure S5. Tauc plots for 1 (up-left), 2 (up-right), 3 (bottom-left) and 4 (bottom-right).




Figure S6. Kinetics of the photocatalysts 1–4 under visible light. The fitting results are represented assuming a pseudo-first order reaction.