



Supplementary Information

Electrospun Magnetic Ionic Liquid Based Electroactive Materials for Tissue Engineering Applications

Liliana . Fernandes ^{1,2}, Rafaela M. Meira ^{1,2,3}, Daniela M. Correia ^{4,*}, Clarisse Ribeiro ^{1,2}, Eduardo Fernandez ⁵, Carmen R. Tubio ⁵ and Senentxu Lanceros-Méndez ^{5,6,*}

¹ Physics Centre of Minho and Porto Universities (CF-UM-UP), University of Minho, 4710-057 Braga, Portugal

² LaPMET-Laboratory of Physics for Materials and Emergent Technologies, University of Minho, 4710-057 Braga, Portugal

³ IB-S-Institute of Science and Innovation for Sustainability, University of Minho, 4710-057 Braga, Portugal

⁴ Centre of Chemistry, University of Minho, 4710-057 Braga, Portugal

⁵ BCMaterials, Basque Center for Materials, Applications and Nanostructures, UPV/EHU Science Park, 48940 Leioa, Spain

⁶ IKERBASQUE, Basque Foundation for Science, 48013 Bilbao, Spain

* Correspondence: dcorreia@quimica.uminho.pt (D.M.C.); senentxu.lanceros@bcmaterials.net (S.L.-M)

Table S1. Electrospinning processing parameters.

Electrospinning processing parameters	
Distance between needle and collector	20 cm
Applied voltage	14 kV
Feed rate	0.4 mL h ⁻¹
Needle diameter	0.5 mm
Collector velocity	1500 rpm
Relative humidity	40 % - 60 %
Temperature	25 °C