

Article

Degradation Rate Control Issues of PEO-Coated Wrought Mg_{0.5}Zn_{0.2}Ca Alloy

Lara Moreno ^{1,2}, Marta Mohedano ^{1,*}, Raul Arrabal ¹ and Endzhe Matykina ^{1,3}

¹ Departamento de Ingeniería Química y de Materiales, Facultad de Ciencias Químicas, Universidad Complutense de Madrid, 28040 Madrid, Spain; lara.morenoturiegano@umons.ac.be (L.M.); rarrabal@ucm.es (R.A.); ematykina@ucm.es (E.M.)

² Materials Science Department, Faculty of Engineering, University of Mons, 20, Place du Parc, 7000 Mons, Belgium

³ Unidad Asociada al ICTP, IQM (CSIC), Grupo de Síntesis Orgánica y Bioevaluación, Instituto Pluridisciplinar (UCM), Paseo de Juan XXIII 1, 28040 Madrid, Spain

* Correspondence: mmohedan@ucm.es

Table S1. Coating surface porosity characteristics from plan view of PEO-T and PEO-S at three treatment times (Figure 3a–c,g–i).

Parameters	PEO-T			PEO-S		
	300 s	600 s	900 s	300 s	600 s	900 s
Thickness (µm)	13.10 ± 1.95	18.34 ± 3.89	16.34 ± 3.04	13.14 ± 1.41	14.88 ± 1.01	18.10 ± 3.95
S _a (µm)	3.94 ± 0.68	2.76 ± 0.30	2.68 ± 0.05	2.47 ± 0.41	2.28 ± 0.21	1.08 ± 0.15
S _{10z} (µm)	12.66 ± 2.62	13.98 ± 0.64	14.78 ± 2.61	11.95 ± 1.51	12.04 ± 0.77	12.47 ± 1.6
Surface pore density (pore/mm ²)	1.09 ± 0.3 · 10 ⁶	8.9 ± 0.9 · 10 ⁵	7.3 ± 1.2 · 10 ⁵	4.97 ± 0.8 · 10 ⁶	4.22 ± 1.5 · 10 ⁶	3.03 ± 0.5 · 10 ⁶
Fraction pore area (%)	15.70	29.84	19.11	4.96	2.52	1.8
Average of pore size (µm)	0.91 ± 0.35	2.53 ± 0.70	1.35 ± 0.23	0.51 ± 0.02	0.24 ± 0.07	0.45 ± 0.08