

Abstract

Mechanical Properties and Structural Requirements of Recycled Aggregate Concrete for Pavements [†]

Onur Ozturk * , Hasan Yildirim, Nilufer Ozyurt  and Turan Ozturan

Department of Civil Engineering, Bogazici University, Istanbul 34342, Turkey; hasan.yildirim@boun.edu.tr (H.Y.); nilufer.ozyurt@boun.edu.tr (N.O.); ozturan@boun.edu.tr (T.O.)

* Correspondence: onur.ozturk2@boun.edu.tr

[†] Presented at the 1st International Online Conference on Infrastructures, 7–9 June 2022; Available online: <https://ioci2022.sciforum.net/>.

Keywords: concrete pavements; recycled aggregates; structural requirements; recycling



Citation: Ozturk, O.; Yildirim, H.; Ozyurt, N.; Ozturan, T. Mechanical Properties and Structural Requirements of Recycled Aggregate Concrete for Pavements. *Eng. Proc.* **2022**, *17*, 27. <https://doi.org/10.3390/engproc2022017027>

Academic Editor: Piergiorgio Tataranni

Published: 2 May 2022

Publisher's Note: MDPI stays neutral with regard to jurisdictional claims in published maps and institutional affiliations.



Copyright: © 2022 by the authors. Licensee MDPI, Basel, Switzerland. This article is an open access article distributed under the terms and conditions of the Creative Commons Attribution (CC BY) license (<https://creativecommons.org/licenses/by/4.0/>).

In recent years, the recycling of waste materials has attracted considerable attention due to the scarcity of natural resources on earth. For instance, researchers have been working on various techniques to utilize construction and demolition wastes as substitutes for natural materials in the construction industry, which is one of the major consumers of natural resources. From this point of view, concrete roads, as one of the most frequently used infrastructural facilities [1] of the construction industry, have significant environmental impacts during their construction period and service life in different aspects. Therefore, great importance should be given to the construction of concrete roads to minimize their environmental impacts, considering their dependence on the high volume of concrete production. Using recycled materials to produce concrete roads is one of the methods implemented in this respect, as their usage provides benefits through natural resources and landfill conservation [2].

The use of recycled aggregates to reduce the environmental impact of concrete is a well-known method, and their impacts on performance have been studied in various respects to date. However, the number of studies on structural requirements of concrete pavements produced with recycled aggregates is very limited. This study aimed to investigate the structural performance of concrete pavements produced with recycled coarse aggregates as a total (100%) and partial (50%) replacement of natural coarse aggregates.

To this end, three different concrete pavement mixtures (Control, RAC-50, and RAC-100) were designed and tested for compressive strength, modulus of elasticity, flexural strength, and density. Then, material parameters obtained from the applied tests were used to determine the required thickness values for a sample pavement (based on IRC 58 [3]), and the results were compared.

According to the test results, the percent reduction compared to control mixture in average compressive strength, modulus of elasticity, flexural strength, and density values were 12.7, 7.7, 16.5, and 2.5 for RAC-50, and 18.9, 14.0, 24.9, and 4.5 for RAC-100, respectively. The test results indicate that the reduction in all the measured parameters increased with an increase in the replacement ratio of natural coarse aggregates with recycled coarse aggregates. The required concrete pavement thickness values for the control, RAC-50, and RAC-100 mixtures were determined to be 18, 20, and 23 cm, respectively (for the sample road and traffic data considered). The required thickness increased with an increase in the amount of recycled aggregate utilized (11% and 25% increase for RCA-50 and RCA-100, respectively). Additionally, concrete pavement thickness values were well-correlated with the flexural strength values obtained for the corresponding concrete mixtures.

To summarize, this study numerically presented the change in the mechanical performance of concrete due to the replacement of natural coarse aggregate with recycled

aggregate and the effect of obtained performance on the thickness requirement of a sample pavement. It should be noted that the test results are dependent on the properties of recycled aggregate used in this study, and various aggregate sources may yield different results.

Author Contributions: Conceptualization, O.O., H.Y., N.O. and, T.O.; methodology, O.O. and H.Y.; validation, O.O., H.Y., N.O. and T.O.; formal analysis, O.O. and H.Y.; investigation, O.O. and H.Y.; writing—original draft preparation, O.O. and H.Y.; writing—review and editing, O.O., H.Y., N.O. and T.O.; supervision, N.O. and T.O. All authors have read and agreed to the published version of the manuscript.

Funding: This research received no external funding.

Conflicts of Interest: The authors declare no conflicts of interest.

References

1. Abut, Y.; Yildirim, S.T.; Ozturk, O.; Ozyurt, N. A comparative study on the performance of RCC for pavements casted in laboratory and field. *Int. J. Pavement Eng.* **2022**, *23*, 1777–1790. [[CrossRef](#)]
2. Ozturk, O.; Yildirim, H.; Ozyurt, N.; Ozturan, T. Evaluation of mechanical properties and structural behaviour of concrete pavements produced with virgin and recycled aggregates: An experimental and numerical study. *Int. J. Pavement Eng.* **2022**. [[CrossRef](#)]
3. Indian Roads Congress. Guidelines for the design of plain jointed rigid pavements for highways (IRC 58). In Proceedings of the Indian Roads Congress, New Delhi, India, June 2015; Fourth revision. Available online: <https://law.resource.org/pub/in/bis/irc/irc.gov.in.058.2015.pdf> (accessed on 5 June 2022).